



Product Information

DPDM-400

High Temperature Silicone Bath Fluid

Operating Temperature Range: 25°C to 250°C (open system) / 25°C to 300°C (closed system)



DPDM-400 Silicone Bath Fluid is recommended for open system baths operating between 25°C to 250°C (open system).

DPDM-400 High Temperature Silicone Bath Fluid is a clear, colorless silicone fluid that is classified as a Dimethyl-Diphenylsiloxane (CAS # 68083-14-7). Characterized by its high flash point, high service temperature range, low vapor pressure, high resistance to oxidation and high resistance to shear, DPDM-400 is an excellent high temperature bath fluid and high temperature heat transfer fluid. .

In open system baths (presence of air), **DPDM-400 High Temp Silicone Bath Fluid** has an operating temperature range of 25°C to 250°C. Although it has a pour point of -30°C, it is not recommended for low temperature bath applications due to its acutely higher viscosities at lower temperatures (see Viscosity/temp specs). In closed system baths*, the operating ranges from 25°C to 300°C.

When compared to Polydimethylsiloxane fluids (PSF-Fluids), **DPDM-400 High Temp Silicone Bath Fluid** exhibits much higher thermal stability as well as resistance to shear and resistance to oxidation.

Bath Applications include: high temperature open system baths, high temperature closed system baths, constant temperature baths, high temperature circulating baths, high temp closed loop baths, high temperature heat transfer baths, high temperature fluids for laboratory research apparatus and instruments.

Features

- Excellent High Temp Performance
- Service range: 25°C to 250°C open system
- Service range: 25°C to 300°C closed system
- High Oxidation Resistance
- Non-Flammable
- High Temperature bath fluid for laboratory research apparatus and instruments.
- High Dielectric strength –dielectric fluid in capacitors
- High Temperature heat transfer applications
- Compatible with virtually all o-rings, gaskets, valves, seals, and hoses *
- VOC Exempt

* Not recommended for silicone o-rings where the fluid may cause swelling

Properties

Appearance: clear, colorless, odorless fluid	<u>Thermal Gel Time (open system)</u> @ 250°C.....1,500 to 2,000 hours @ 260°C.....>200 hours
Pour Point °C.....-30°C	<u>Specific Heat</u> @ 25°C.....0.35 cal/g°C, 25°C
Flashpoint.....315°C	Thermal Expansion (cc/cc °C).....0.00073
Specific Gravity.....1.07	Thermal Conductivity (cal/cm/sec °C).....0.00032
Refractive index.....1.505	Surface Tension (dynes/cm).....25.2
<u>Volatility, % wt loss</u> 24 hours @ 150°C.....max 0.3%	
<u>Dielectric Properties</u> Breakdown Voltage (KV/2.5mm)....>50 Dielectric Constant (50 Hz).....2.88 Dissipation Factor (50 Hz).....<0.0005	

Viscosity/Temp Specs.

Viscosity/Temp Coefficient.....0.82

Viscosity @25°C.....400cSt (mm2/sec)

Viscosity @ temperature
 @250°C.....7cSt (mm2/sec)
 @ 200°C.....11cSt
 @100°C.....46cSt
 @50°C.....167cSt
 @25°C.....400cSt
 @ 0°C.....1,770cSt
 @ -25°C.....24,800cSt

Packaging

1-gallon.....4kg net wt.
 5-gallon pail.....20kg net wt.
 55-gallon drum.....200kg net wt.

F.O.B. Phila, PA U.S.A.

For More Info, Contact:

Clearco Products Co., Inc.

15 York Road
 Willow Grove, PA 19090
 U.S.A.

Tel: (215) 366-7860

Fax: (215) 366-7862

Email: info@clearcoproducts.com

Web: www.clearcoproducts.com