



Product Information

Pure Silicone Fluids (standard viscosities)

100% PDMS Silicone CAS # 63148-62-9 Viscosities: 50cSt, 100cSt, 200cSt, 350cSt, 500cSt, 1,000cSt



Pure Silicone Fluids are linear 100% Polydimethylsiloxane aka PDMS Silicone fluids (CAS # 63148-62-9)

Pure Silicone Fluids are linear 100% Polydimethylsiloxane Fluids aka PDMS Silicone (CAS # 63148-62-9) that range in viscosity from 50cSt (centistokes) to 1,000cSt.

These fluids are characterized by their medium viscosity, wide service temperature range, low V.T.C. (little viscosity change at both low and high temps), high damping action (meet VV-D-1078 Silicone as damping fluid), excellent lubricity for rubber and plastics, high dielectric strength, high resistance to shear, and high resistance to oxidation.

Pure Silicone Fluids are compatible with virtually all o-rings, gaskets, valves and seals with the exception of silicone o-rings*.

Pure Silicone Fluids are Thermally Stable, showing excellent stability in low and high temperatures applications for long periods of time. They will remain stable in open system (presence of air) @ 150°C / 302°F. In closed systems, their service temperature is even higher.

Uses include: Damping Fluids, Bath Fluids, Heat Transfer Fluids, Hydraulic Fluids, Dielectric Fluids, Plastic & Rubber Lubricants, O-Ring Lubricants, gaskets lubricants, valve and seal lubricants.

**Silicone fluids can cause swelling in silicone o-rings.*

Synonyms: PDMS, Dimethyl fluids, polydimethylsiloxane, Dimethylpolysiloxane

Specifications

Chemical Name	Polydimethylsiloxane PDMS Silicone Oil
CAS #	63148-62-9
Product Code	PSF-50cSt PSF-100cSt PSF-200cSt PSF-350cSt PSF-500cSt PSF-1,000cst
Appearance	Clear, colorless fluid
Federal spec met	VV-D-1078
Minimum Order	1-gallon (3.785 liters)

Features

- Clear, colorless, odorless fluids
- Excellent Lubrication for plastic and rubber
- High Damping Action...meets VV-D-1078 "Silicone as damping fluid."
- Wide service temperature range -40°C to 150°C (open system), -40°C to 230°C (closed system)
- Excellent Thermal Stability
- High water repellency
- High oxidation resistance
- High dielectric strength
- High resistance to shear
- Inert lubricant for o-rings, gaskets, valves and seals.

Typical Product Data

Viscosity (cSt)	Specific Gravity	Refractive Index	Pour Point (°C)	Flash Point °F (open cup)	V.T.C	Surface Tension	Thermal Expansion (cc/cc/c 0-150°C)	Thermal Conductivity g cal/cm•sec• °C	Maximum Volatility @ 150°C (%wt)	Specific Heat BTU/lb. °F
50	0.960	1.402	-55°C	285°C	0.59	20.8	0.00106	0.00036	0.5	0.36
100	0.966	1.4030	-55°C	315°C	0.60	20.9	0.00096	0.00037	0.5	0.36
200	0.968	1.4031	-50°C	315°C	0.60	21.0	0.00096	0.00037	0.5	0.36
350	0.970	1.4032	-50°C	315°C	0.60	21.1	0.00096	0.00037	0.5	0.36
500	0.971	1.4033	-50°C	315°C	0.60	21.1	0.00096	0.00038	0.5	0.36
1,000	0.971	1.4035	-50°C	315°C	0.61	21.2	0.00096	0.00038	0.5	0.36

Packaging:

1-gallon (3.785 liters).....	8lbs/ 3.6kg net wt.
5-gallon pail (18.9 liters).....	40 lbs / 18kg net wt.
55-gallon drum	440 lbs / 200kg net wt.
275-gallon IBC Tote.....	2,204 lbs / 1,000kg net wt.
F.O.B. Phila, PA U.S.A.	

For More Info, Contact:

Clearco Products Co., Inc.

15 York Road
Willow Grove, PA 19090
U.S.A.

Tel: (215) 366-7860

Fax: (215) 366-7862

Email: info@clearcoproducts.com

Web: www.clearcoproducts.com