

Pure Silicone Fluid 2cSt Dodecamethylpentasiloxane

Super Low-Viscosity Silicone: >90% Dodecamethylpentasiloxane CAS# 141-63-9



Pure Silicone Fluid 2cSt possesses excellent low temp stability

Pure Silicone Fluid 2cSt (PSF-2cSt) is a super low-viscosity linear Polydimethylsiloxane that is primarily Dodecamethylpentasiloxane (CAS#141-63-9). The product is clear, colorless and odorless with a viscosity of 2cSt (centistokes) @ 25°C.

PSF-2cSt is characterized by its low viscosity, high rate of evaporation, low pour point (-100°C), low VTC (viscosity change at temperature), low surface tension (high spreadability), high damping action (meets federal spec VV-D-1078 "Silicone as Damping Fluid" and excellent lubrication. In closed systems, it is an excellent low temperature bath fluid.

PSF-2cSt (Dimethicone) is also used in a number of personal care products due to its excellent spreading and unique volatility characteristics. It features good solubility in anhydrous alcohols and in a wide variety of solvents. In addition, it leaves no residue or build-up, has a transient effect, and a non-greasy feel. Products include: antiperspirants, deodorants, skincare lotions, suntan lotions, cosmetics etc.

Specifications

Chemical family	Polydimethylsiloxane
Chemical name	Dodecamethylpentasiloxane
CAS No.	CAS# 141-63-8
INCI Name	Dimethicone
Appearance	Clear, colorless, odorless fluid
Flammability	HMIS 3
Meets NSN	NSN 9150-00-754-2600
Federal Spec	VV-D-1078 Silicone as damping fluid
Minimum Order	1-gallon

Features

- Super low viscosity
- Excellent Lubrication
- Excellent Low Temperature Serviceability
- Pour Point: - 100°C Pour Point
- High Damping action...meets VV-D-1078 Silicone as damping fluid
- clear, colorless, odorless fluid
- High Compressibility
- High Oxidation Resistance

VOC-Exempt

- VOC Exempt
- Excellent Carrier alternative to non-VOC Compliant solvents and petroleum distillates
- Add to non-VOC compliant formulations to achieve compliancy

Typical Product Data

Viscosity	Specific Gravity	Viscosity-Temp Coefficient	Flash Point	Pour Point	Refractive Index	Thermal Expansion cc/cc °C	Thermal Conductivity g/cal/cm/sec °C	Surface Tension	Dielectric Constant	Dielectric Strength volts/mil
2cSt	0.873	0.48	75°C	-100°C	1.3900	0.00117	0.00026	18.7	2.45	350

Product Data (cont'd)

Boiling Point	Vapor Density (air = 1)	Vapor Pressure @ 25°C	Evaporation rate Butyl acetate = 1	Molecular weight
229°C	>1	1mmHg	<1	410

CAS Information

Identity	CAS #	%
Dodecamethylpentasiloxane	141-63-9	>90%
Decamethyltetrasiloxane	141-62-8	<10%
Octamethylcyclotetrasiloxane	556-67-2	<10%

Packaging

1-gallon pail.....	2.5kg
5-gallon pail.....	.5kg
55-gallon drum.....	170kg
Terms: F.O.B. Phila, PA U.S.A.	

For More Information, Contact:

Clearco Products Co., Inc.

3430 G. Progress Drive

Bensalem, PA 19020

Tel: 215 639-2640

Fax: 215 639-2919

Email: info@clearcoproducts.com

Web: www.clearcoproducts.com