

Product Information

PSF-100,000cSt Pure Silicone Fluid

100% Polydimethylsiloxane / PDMS Silicone Fluid CAS # 63148-62-9



Pure Silicone 100,000cSt is a high viscosity PDMS silicone that meets VV-D-1078 "Silicone as Damping Fluid"

PSF-100,000cSt Pure Silicone Fluid is a clear, colorless, odorless high viscosity 100% linear Polydimethylsiloxane Silicone / PDMS Silicone (CAS # 63148-62-9 with a viscosity of 100,000cSt (centistokes) @ 25°C.

PSF-100,000cSt Pure Silicone Fluid is characterized by its high damping action, high resistance to oxidation, excellent lubricity, wide service temperature range, low VTC (little viscosity change at both high and low temperatures), high dielectric strength and high resistance to shear.

PSF-100,000cSt Silicone Fluid meets Federal Specification VV-D-1078 "Silicone as Damping Fluid". It is used in a wide range of military, industrial and avionic gauges, meters, instruments, and monitoring systems.

In addition, Pure Silicone Fluid 100,000cSt is inert to virtually all plastic, rubber and metal surfaces. It is widely used as a lubricant for o-rings, gaskets, valves and seals.

<u>Uses include</u>: High Damping Action Fluid, Dielectric Fluid, Lubricant for Rubber and plastics, O-Ring Lubricant, Valve and Gasket lubricant.

Specifications

Product code	PSF-100,000cSt
Chemical Name	Polydimethylsiloxane
INCI Name	Dimethicone
CAS#	63148-62-9
Appearance	Clear-colorless fluid
Minimum Order	1-gallon

Environmental & VOC Status

Clearco Pure Silicone Fluids are exempt from Federal VOC Regulations, including California (CARB) and OTC Regulations. It does not contribute to ozone depletion and global warming. In addition, it meets the following:

- RoHS Compliant
- HAP-free
- VOC Exempt

Features

•	High Viscosity Index	•	High Damping Action
•	Excellent Lubrication	•	Meet VV-D-1078
•	Non-Flammable	•	Excellent Thermal
•	High Resistance to		Stability
	Oxidation	•	High Water Repellency
•	High Resistance to Shear	•	High Compressibility
•	Chemically Inert		

Packaging

1-gallon	8lbs / 3.6kg net wt.
5-gallon pail	40lbs / 18kg net wt.
55-gallon drum	419lbs / 190kg net wt.
F.O.B. Phila, PA	A USA

Typical Product Data

. ypicai i	Todact Date	•						
Specific Gravity	Refractive Index	Pour Point	Flash Point	Surface Tension	Thermal Expansion cc/cc °C	Thermal Conductivity g/cal/cm/sec °C	Maximum Volatility % Wt @ 150°C	V.T.C.
0.977	1.4035	-41°C	321°C	21.5	0.00094	0.00038	0.23	0.61

Dielectric Properties

ĺ	Dielectric Constant	Dielectric Strength	
	50Hz	volts/mil	
ĺ	2.75	400	

For More Info, Contact: Clearco Products Co., Inc.

15 York Road Willow Grove, PA 19090 U.S.A.

Tel: (215) 366-7860 Fax: (215) 366-7862

Email: info@clearcoproducts.com
Web: www.clearcoproducts.com

^{*} Not recommended for silicone rubber as swelling may occur